



MICRODUCT NESTOR OPTIMUS DB N X 7/3,5 MM + N X 14/10 MM



Application	Microduct / duct bundle for direct buried installation or installation in existing protective pipes or cable shafts.		
Construction	Material	The individual ducts are made of HDPE.	
	Colour coding	The ducts are colour-coded according to customer specifications, FIN 2012, ANSI/TIA, IEC or other.	
	Trace wire	Duct bundles can be equipped with a tracer wire according to customer specifications.	
	Outer sheath	The duct bundles are sheathed with a common HDPE sheath. The nominal sheath thickness is $1,0 \pm 0,1$ mm. Sheath marking is printed on one-meter intervals. The sheath marking is printed according to customer specifications.	

Nominal dimensions of bare duct without outer sheath				
Duct type	Dimensions [mm]		Weight [kg/km]	Tensile strength
	Outer Diameter	Wall Thickness		
7/3,5 mm	$7,0 \pm 0,2$	1,7...1,8	27,5	270 N
14/10 mm	$14,0 \pm 0,2$	1,9...2,2	72	700N

Nominal dimensions of ducts and duct bundles with outer sheath					
Configuration		Diameter [mm]		Weight [kg/km]	Tensile strength
Count	Grouping	Duct OD	Maximum OD		
12+2	12 x 7/3,5mm + 2 x 14/10 mm	$7,0 \pm 0,2$ $14,0 \pm 0,2$	38,7	562	5500 N
24+1	24 x 7/3,5mm + 1 x 14/10 mm	$7,0 \pm 0,2$ $14,0 \pm 0,2$	43,5	870	8490 N

Temperature ranges		
Temperature range	Installation	-15 - +40 °C
	Transport, storage and operation	-45 - +60 °C

Mechanical characteristics			
Characteristics	Test Methods	Descriptions	Requirements
Tensile strength (*)	IEC 60794-1-21, method E1	Test length >1 m Duration 10 min	Load = 9,81 x W [N] W = mass of 1 km [kg/km]
Bending (cold) (*)	IEC 60794-1-21, method E11B	Temperature -15 °C Cycles 10	Mandrel diameter 30 x OD
Repeated bending (*)	IEC 60794-1-21, method E6	Load 20 N Cycles 35 Time per cycle ~2 s	Bending diameter 30 x OD
Impact (*)	IEC 60794-1-21, method E4	Anvil diameter 50 mm Surface radius 300 mm Recovery time 1 hour	Impact energy 5 J
Torsion (*)	IEC 60794-1-21, method E7	Test length 1 m Load 20 N Cycles 5	Number of turns ±1 (360° in both directions)
Kink (*)	IEC 60794-1-21, method E10	Temperature 20 °C	Loop diameter 20 x OD
Crush (*)	IEC 60794-1-21, method E3	Duration 1 min Recovery time 1 hour	Load (plate/plate) 2000 N
Pressure withstand (**)	IEC 60794-1-22, method F13	Test length 1 m Temperature 60 °C Duration 30 min	Pressure (water) 15 bar
Coefficient of friction (COF)	S 201-10150	Wheel Test Without adding lubricant	≤ 0,1

Acceptance criteria:

(*) After the test, under visual examination, without magnification, there shall be no damage and the tested sample shall pass the inner clearance test (***). If a recovery time is defined, the inner clearance test is done after the recovery time.

(**) Under visual examination, without magnification, there shall be no damage to the tested microduct.

(***) Inner clearance test is done by passing a metal sphere through the tested section of microduct or microduct assembly. The minimum diameter of the sphere is 85% of the nominal microduct bore diameter (ID). The test is passed if the sphere passes through the microduct.